



KMG-BX

Certificate of Analysis

CHEMICAL ANALYSIS (%)				
Item	KMGBX 75	KMGBX 85	KMGBX 86	KMGBX 87
Al ₂ O ₃	Min. 75	Min. 85.0	Min. 86.0	Min. 87.0
SiO ₂	Max. 19.0	Max. 9.0	Max. 8.0	Max. 7.0
CaO	Max. 0.5	Max. 0.5	Max. 0.5	Max. 0.5
Fe ₂ O ₃	Max. 2.5	Max. 2.0	Max. 1.8	Max. 1.8
TiO ₂	Max. 4.0	Max. 4.0	Max. 4.0	Max. 4.0
PHYSICAL PROPERTIES				
BULK DENSITY (g/cm ³)	Min. 2.8	Min. 3.10	Min. 3.15	Min. 3.20
APPEARANCE	Gray and black opaque particles			
GRAIN SIZE (mm)	3-5, 1-3, 0-1, Powder 200 Mesh			

The technical data represent the average of current production. During the test has to be considered a fluctuation of these values $\pm 0.5\%$.